

Properties Comparison

Liquidmetal and Common Crystalline Metals

	Mechanical and Physical Properties				
	Liquidmetal® Alloy	Mg AZ-91	Al 380 Series	Ti 6Al-4V	Stainless 17-4
Yield Strength, σ_y <i>ksi</i> (MPa)	270 (1900)	22 (150)	23 (159)	115 (790)	126 (870)
Hardness <i>Vickers</i>	550	71	100	340	325
Density, ρ <i>lb/in³</i> (g/cm³)	0.222 (6.1)	0.065 (1.8)	0.099 (2.8)	0.160 (4.4)	0.283 (7.8)
Impact Strength <i>ft-lb</i> (J)	5.9 (8)	1.9 (2.7)	3.0 (4)	17.7 (24)	55.3 (75)
Elasticity, e (% of Original Shape)	2.00%	0.35%	0.10%	0.69%	0.44%
Young's Modulus, E <i>Msi</i> (GPa)	13.5 (93)	6.5 (45)	10 (71)	16.5 (114)	28.6 (198)
Specific Strength, σ/ρ <i>ksi</i> (MPa)	45 (311)	13 (83)	8 (58)	26 (178)	16 (111)
Poisson's Ratio, ν	0.39	0.35	0.33	0.34	0.27

	Electrical and Thermal Properties				
	Liquidmetal® Alloy	Mg AZ-91	Al 380 Series	Ti 6Al-4V	Stainless 17-4
Heat Capacity, cp <i>BTU/lb°F</i> (J/Kg°K)	0.10 (420)	0.25 (1050)	0.23 (963)	0.13 (526)	0.10 (419)
Thermal Expansion, α <i>$\mu\text{in/in}^\circ\text{F}$</i> ($\mu\text{m/m}^\circ\text{K}$)	5.5 (10.1)	14.0 (26.0)	12.0 (21.2)	4.8 (8.6)	6.7 (12.0)
Thermal Conductivity, k <i>BTU/ft hr°F</i> (W/m²K)	3.5 (6)	42.1 (73)	62.9 (109)	3.8 (7)	10.3 (18)
Electrical Resistivity, R <i>$\mu\Omega\text{ in}$</i> ($\mu\Omega\text{ cm}$)	75 (190)	6.7 (17)	2.5 (6.4)	70 (178)	30.3 (77)

Properties listed in this chart are for the following materials:

Magnesium AZ-91D

Aluminum 380.0-F

Titanium Ti-6Al-4V ELI, Annealed

Stainless Steel 17-4 PH Condition H 1150

Liquidmetal Technologies (LQMT) does not warrant or guarantee that the data, advice, or recommendations generated by any of the LQMT GENERAL GUIDELINES are complete or appropriate for any particular application. LQMT is not responsible for any damages or loss you may suffer as a result of using any of the GENERAL GUIDELINES to process Liquidmetal® alloys. No statement or recommendation contained in any of the GENERAL GUIDELINES is intended to, or should be construed to, grant any license under any patent or other intellectual property right of LQMT or any of its subsidiaries or affiliates. For additional GENERAL GUIDELINES and Technical Support, please call our Corporate Office in Rancho Santa Margarita, CA (USA) at Tel (949) 635-2100 or Fax (949) 635-2188.